

# WT23DE03

## Cotton Denim



CHARACTERISTICS	
COMPOSITION	24% recycled cotton / 24% OCS virgin cotton / 52% virgin cotton
WEIGHT	465 g/m <sup>2</sup>
USABLE WIDHT	158 cm
ORIGIN	Italy
DYEING PROCESS	Indigo dye – Ready to wash
FIRE RESISTANT (FR)	No
CERTIFICATIONS	Yarn: GRS Virgin fiber: OCS

RECOMMENDED CARE
Wash at 40° - Do not bleach - Do not tumble dry - Iron hot (max 150°C) - (P) Professional cleaning with any solvents except Trichloroethylene

COMPLIANCE & TRACEABILITY
This fabric has been weaved with recycled yarns coming from unsold products and rolls of fabrics. This is why, due to the mechanical recycling process, residual fibers may be found in the fabrics.

## QUALITY CONTROL

<b>FIBER COMPOSITION</b>	0%	ISO 1833-1
<b>DISTORSION</b>	0,3%	BS EN ISO 13015

<b>ABRASION</b>	> 10 000 runs	ISO 12947-1 ISO 12947-2
<b>PILLING</b>	4	ISO 12945-2 ISO 12945-4

	<b>Warp</b>	<b>Weft</b>	<b>Standards</b>
<b>SHRINKAGE</b> <i>(Free-steam)</i>	+ 3%	0%	ISO 3005
<b>SHRINKAGE</b> <i>(Professional cleaning)</i>	+ 1,1%	- 0,1%	ISO 3175-1
<b>SHRINKAGE</b> <i>(Washing)</i>	+ 1,5%	- 1%	ISO 6330
<b>SLIPPAGE</b>	3 mm	1 mm	ISO 13936-2

## COLORFASTNESS

ARTIFICIAL LIGHT	4/5	ISO 105-B02
DRY RUBBING	3	UNI EN ISO 105-X12
WET RUBBING	1	UNI EN ISO 105-X12
ACID PERSPIRATION	4/5	UNI EN ISO 105-E04
ALKALINE PERSPIRATION	4/5	UNI EN ISO 105-E04
DOMESTIC AND COMMERCIAL LAUNDERING	4/5	UNI EN ISO 105-C06

## CHEMICAL

PH	6,6 UPH	ISO 3071
FORMALDEHYDE	<16 MG/KG	ISO 14184-1
AZO DYES	<5 MG/KG	UNI EN ISO 14362-1
ODOUR	ODOURLESS	GB 18401-2010 SECTION 6.7



Paris Trade and Companies Register under number 842 426 769

Nona Source – 12 rue Philippe de Girard – 75010 Paris – France

VAT Number: FR27842426769

[contact@nona-source.com](mailto:contact@nona-source.com)